

P754 – Textured Black



Product Description

P754 is a textured single component black meticulously formulated to replicate the authentic texture of plastic surfaces.

This product restores the original appearance of plastic components to their factory-like aspect, and exhibits excellent adhesion without the need for additional adhesion promoters to plastic substrate.

Adjustments can be made to the coarseness desired by changing the dilution ratio % as described below.

P754 may serve as a primer in conjunction with HYMAX solvent-borne coatings after light scuffing with Scotch Brite.

However, P754 should not be topcoated with Hydrobase.

Extra Comments

No additional top-coating is necessary with P754, as it boasts good resistance to both UV rays and chemical exposure.

Product Application



Scuff surface with a fine pad soaked in GenClean degreaser.



Wipe-on with GenClean degreaser and then wipe-off promptly while the degreaser remains wet on the panel.



| | P754 | HYMAX Thinner |
|---------------------------|-------------|----------------------|
| For coarse texture | 100% | 0% |
| For fine texture | 100% | 40% |

Apply the percentage of thinner you need (0 - 40%) based on your texture requirement.




HVLP 1.6 – 1.8 mm.
3.0 – 3.5 bar.

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.

P754 – Textured Black



2- 3 medium coats of 9754.



Between coats, flash off for 5 minutes.



Wear suitable protection and for more information on safety, check the product's Safety Data Sheet.

Product Characteristics

| | |
|--------------------------|---|
| VOC(2004/42/EC): | 2004/42/EC IIB (e) (840)656. The EU limit value for this product (product category IIB. e) in ready to use form is max 840g/l. The VOC content of this product in ready to use form is max. 656g/l. |
| Specific Gravity: | 1.05 kg/cm ³ . |
| Flash Point: | 25°C (86 °F). |
| Solid Content: | 33.1 % by weight. |
| Coverage: | 5-6 m ² /l (theoretical). |
| SDS: | Refer to the Safety Data Sheet. |
| Shelf life: | 18 months. |

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.